

## Model 295 Series Clean Phone® Solvent Resistance

**The GAI-Tronics Clean Phone® faceplate overlay withstands exposure of more than 24 hours duration under DIN 42 115 Part 2 to the following chemicals without visible change:**

|                                     |                                     |
|-------------------------------------|-------------------------------------|
| 1.1.1. Trichloroethane (Genklene)   | Hydrogen Peroxide <25%              |
| Acetaldhyde                         | Isophorone                          |
| Acetic acid <50%                    | Isopropanol                         |
| Acetone                             | Lixtop                              |
| Acetronitrile                       | Methanol                            |
| Aliphatic hydrocarbons              | Methylethylketone                   |
| Ammonia <32%                        | Methylisobutileketone               |
| Ammonium chloride <10%              | N-Butyl acetate                     |
| Amylacetate                         | Nitric acid <10%                    |
| Butylcellosolve                     | Oleic acid                          |
| Cyclohexanol                        | Peracetic Acid                      |
| Cyclohexanone                       | Petrol                              |
| Diabasic Ester 5                    | Phosphoric acid <30%                |
| Diacetone alcohol                   | Potassium carbonate                 |
| Dibutyl Phthalate                   | Potassium ferrocyanide/ferricyanide |
| Dichromate                          | Potassium hydroxide <40%            |
| Dichromate                          | Saturated Salt Solution             |
| Diethyl ether                       | Silver Nitrate                      |
| Diocetyl Phthalate                  | Skydrol 500B4                       |
| Dowanol DRM/PM                      | Sodium bisulphate <50%              |
| Ethanol                             | Sodium carbonate (saturated)        |
| Ether                               | Sodium hydroxide 50%                |
| Ethylacetate                        | Sodium hypochlorite <20% (Bleach)   |
| Ferric Chloride                     | Sulfuric acid <30%                  |
| Ferric Chloride (saturated)         | Tego 51                             |
| Ferrous Chloride (saturated)        | Turpentine substitute               |
| Formic acid <50%                    | Toluene                             |
| Fromaldehyde (37%-42%) <sup>1</sup> | Triacetin                           |
| Glutaraldehyde 50% in water         | Trichloracetic acid <50%            |
| Glycerine                           | Water                               |
| Glycol                              | White Spirit                        |
| Hydrochloric Acid <36%              | Xylene                              |

<sup>1</sup> Initial white staining; fades after 24 hours

**The GAI-Tronics Clean Phone® faceplate overlay is NOT resistant to the following chemicals:**

Benzoyl alcohol  
Concentrated caustic solution  
Concentrated mineral acids  
Dichloromethane  
Dimethylfromamide  
High pressure steam at over 100°C  
Methylene chloride  
Tetrahydrofuran

In common with all polyester based products, the overlay is not suitable for use in conditions of long term exposure to direct sunlight (UV).

**The GAI-Tronics Clean Phone® faceplate overlay withstands 24 hours exposure to the following reagents at 50°C without visible staining:**

Bleach/toilet cleaner  
Cream cleaners  
Furniture polish  
Hard surface cleaner (kitchen and bathroom)  
Surface cleaner containing ammonia  
Vinegar  
Washing liquid  
Washing powder solutions  
Window cleaner

**Please contact the factory, at 1-800-492-1212 or sales@gai-tronics.com, with questions pertaining to chemicals or conditions not listed.**

<sup>1</sup> Initial white staining; fades after 24 hours

Revised 8/16/2016